ALLIGATOR macht's einfach

Kieselit-Klima-Farbe LEF

Ready for use sol-silicate interior paint in compliance with DIN 18363. Corresponds to opacity class 1 and wet scrub resistance class 1. Silicification on mineral substrates, perfect adhesion on organic substrates. The application in system with Klieselit-Klima-Spachtel provides a sustainable biocide-free protec-



Product characteristics

Properties	 Highly diffusible For a comfortable room climate Highly hard-wearing Resistant to disinfectants as per test certificate Tested at German Committee for Health-Related Evaluation of Building Products AgBB Without the addition of preservatives Solvent- and plasticizer-free Free of fogging-active substances Tox-free as confirmed by German TÜV-certificate
Areas of application	Interior only
Suitable substrates in detail	 Surfaces prone to mildew and fungal infestation In system with Kieselit-Klima-Spachtel / Klima-Mörtel Suitable for damp rooms as the coating is not a breeding ground for mildew. New woodchip wallpapers and glass fabrics Highly sensible living quarters (e.g. schools, nurseries, etc.) Stressed wall surfaces

Material description

Ingredients	Titanium dioxide
-	Fillers
	Additives
Density	1.5 kg/l
Water vapour permeability	< 0,01
Maximum particle size	Fine
Wet scrub class	1
Opacity class	1 at 7 - 8 m²/L
Average consumption (short text)	approx. 130 - 150 ml/m²
Average consumption	It is advisable to determine the exact consumption figure by producing a sample area.
	The consumption varies depending on the application technique and the substrate. It is therefore advisable to de- termine the exact consumption figure by producing a sample area.
Colour shade	White
Suitable tinting paints	Kieselit full colour and tinting paints or ready-mixed at the factory. Base 1 - 3 products with system-matching tinting pastes of the ALLFAcolor range. Please note that with tinted products the specified properties may change.



Kieselit-Klima-Farbe LEF

Gloss level	Dead matt according to EN 13300
Storage	Cool, but protected from frost
Thinning	Kieselit-Grundiermittel mixed with water at a ratio of 1:1.
Substrates	
Substrates	
Suitable substrates	 All usual mineral substrates (renders/plasters, concrete, masonry) Gypsum wallboards and gypsum plasterboards Gypsum plaster Solid mineral and organic existing paint layers Woodchip wallpaper Glass fabrics
Substrate conditions	The substrate must be clean, dry, firm and sound. Follow the building regulations (in Germany VOB, Part C, DIN 18363, Section 3). Inside renovation coatings can normally be carried out without a special priming coat. For new coatings the surface has to be first attended with an appropriate primer of the ALLIGATOR – product range, following the technical specifications.
Substrate conditions	Gypsum blocks Adjust the primer to absorbency. With coatings destined to bridge capillary cracks, reinforce completely using a fleece. In addition the guidelines of BFS-Fact Sheet No. 17 apply.
	Gypsum building boards (interior) Adjust the primer to absorbency. With coatings destined to bridge capillary cracks, reinforce the entire surface using a fleece. In addition the guidelines of BSF Fact Sheet No. 12 apply. Ingredients which might penetrate have to be isolated before following coatings.
	Gypsum plaster, gypsum sand plasters etc. Remove any sintered layers. For first coatings take care of a sufficient penetration of the primer (e. g. by using a penetrating primer). Additionally the guidelines of BFS Fact Sheet No. 10 apply.
	Derived timber products (chipboards, OSB-boards etc.) - interior Have to be covered with a suitable gypsum board or gypsum fibre board as otherwise cracks may occur in the area of butt-joints.
	Aerated concrete - interor: In case of rooms of high humidity, external walls have to be additionally treated by a moisture guard, applied onto their insides. This can be effected applying a two-component coating like e.g. Hydropox. In addition the guidelines of BFS Fact Sheet No. 11 apply.
	Base renders (interior): Mineral base renders must be thoroughly cured and dry, because otherwise discolouration, in particular with tinted following coats, may occur. As a rule of thumb assume 1 day drying time per mm of layer thickness, but correspondingly longer at low temperatures and high humidity. Excessive temperatures and low relative humidity also lengthen the setting process. Treat replastered locations with fluosilicate. In addition, the guidelines according to BFS Fact Sheet No. 10 apply.
	Concrete Remove forming oil, grease and wax by washing with surfactant. Remove any sintered layers mechanically. Check the absorbency of the concrete by wetting tests. In addition, the guidelines according to BFS Fact Sheet No.1 apply for exterior coatings and the guidelines according to BFS Fact Sheet No. 8 for interior coatings.
Application	
Application method	Application by brush, roller or spraying
Coating system	Initial coatings Priming coat with Kieselit-Grundierfarbe or Kieselit-Grundiermittel thinned with water 1:1. Intermediate coating thinned to max. 3%. Finishing coating preferably unthinned.

Technical Data Sheet



Kieselit-Klima-Farbe LEF

	Recoatings Priming coat with Kieselit-Grundierfarbe or Kieselit-Grundiermittel thinned with water 1:1. With solid and sound substrates a priming coat can be omitted. Apply Multi-Grund 3 in 1 LEF or Grundweiß LEF as priming coat for organic substrates. Intermediate coating thinned to max. 3%. Finishing coating preferably unthinned.
	Due to the great varieties of our range and specific applications it is also possible to use other primers or coating systems. For this please contact our technical service.
Application	When painting pay attention to spread the material liberally and evenly in order to achieve a coat thickness which is necessary for the visual appearance and durability.
Application hints	In case of increased load two paint layers might be necessary.
Note	Check tinted paint for colour accuracy prior to the application. Objections regarding the colour shade cannot be accepted after the application.
	The figures given for parameters are average values. Due to the use of natural raw materials in our products, the actual value determined on the individual supplied product may differ slightly without affecting its suitability. These date refer to the white respectively standard product. Tinting may cause deviations.
	Plasto-elastic joints should not be coated as the higher elasticity of the sealing mass might cause cracks or discol- ouration of the coating. In individual cases tests have to be carried out to judge the suitability.
	With coatings on woodchip wall paper, natural wood constituents in combination with silicate paints, may cause yellowish brown discolouration. These areas may be isolated selectively with Iso-Grund.
	On smooth surfaces and under adverse light conditions, an irregular suface is normal and cannot always be avoided.
	With varying absorptivity and substrate moisture as well as with alkalinity, the chemical binding process - particularly with tinted products - may provoque irregular drying.
	Adjacent areas, particularly glass, ceramics, clinker, need to be masked carefully, as the product may affect the surface.
Practical hints	Repairs Touching up surfaces may be more or less visible, even with using the original coating material. Traces are unavoid- able according to BFS Fact Sheet No. 25. Whether a repair is considered as optically disturbing is depending on many parameters, like colour shade, gloss level, layer thickness, substrate, illumination etc. It is advisable to apply a test coating on inconspicuous places.
	Colour Accuracy / Metamerism The perception of colour shades is influenced by various parameters, such as light, gloss, angle, structure. Substrates of different degrees of irregularities may have different effects despite having been coated with the same material. Coating materials of the same hue but of different gloss levels also appear to be different. Various materials of the same colour shade that appear to be matching by daylight may show strong deviations in artificial light (metamerism effect). In case of increased requirements on matching colours of different building parts, materials and / or surfaces, the BFS Fact Sheet No. 25, section 4.2.2. can be taken into consideration.
	Fogging The phenomenon of suddenly occuring black dust deposits on interior surfaces (fogging effect) has not yet been fully elucidated. As a preventive, the Federal Environment Agency (Umweltbundesamt) recommends to only use low-emission, in particular plasticizer-free products. These products are solvent- and plasticizer-free. The absence of fogging cannot be ensured.
	New mineral Substrates New mineral substrates may only be coated after setting and drying, not earlier than after 14 days, better after 4 weeks. In unfavourable drying conditions, the waiting period can be prolonged.
	Non-combustibility According to DIN 4102 (in Germany) the construction material class A (non-combustibility) is retained with usual mineral substrates such like renders/plasters, concrete and also gypsum plasterboard with enclosed surface, even if their surfaces are coated with dispersion based paints. For usability certificate as non-combustible system for interiors with ALLFAtexx glass fibres and fleeces refer to the general construction supervision test report.



Kieselit-Klima-Farbe LEF

	Hairline Crack bridging Coatings on Gypsum Plasterboard In correspondance with the building regulations (in Germany VOB/C DIN 18363, Section 3.2.1.2) hairline crack bridging coatings on gypsum plasterboards and gypsum fibreboards can only be realized by the additional embed- ding of a fleece. Sidelight
	Unfavourable lighting conditions (sidelight) may occur for instance after the subsequent installation of lights. This fact must be known before works. Specific requirements on evenness and uniformity of the coating have to be previously agreed upon.
Temperature limit	Between+ 8° C and + 30° C for substrate and ambient air during processing and drying.
Drying time	At + 20 ° C for substrate and ambient air and 65% relative humidity (RH), recoatable after approx. 4 - 5 hours. Lower temperature or a higher humidity extend the drying time.
Tool cleaning	Immediately after use with water and soap
Information	
-	
Product code	BSW40 (M-SK01)
General information	Keep out of reach from children. Ensure good ventilation during use and drying. Do not eat, drink or smoke while using the product. In case of contact with eyes or skin, immediately and thoroughly rinse with water. Do not allow to enter drains, waterways or soil. Clean tools immediately with water and soap. The coating material is highly alkaline. Therefore protect skin and eyes from paint splashes.
Declaration of ingredients	Styrene dispersion, potassium water glass, titanium dioxide, calcium carbonate, siliceous fillers, water, additives
Observe safety data sheets	Further details: See Safety Material Data Sheet (MSDS)
Category VOC	EU limit value for the VOC contents of this product: (Category A/a) 30 g/l (2010). This product contains max.
VOC content (in gram per litre)	< 1 g/l
WHC	1 (weakly water-polluting)
Waste disposal	Only completely emptied containers should be given for recycling. Dispose containers with residues of liquid product via waste collection point accepting old paints and enamels. Dispose dried hardened product residues as construction site/demolition/ municipal or domestic waste.
Container size	

Content	EAN code	Article no.
12,5 L	4002822019525	845469

System specific and system completing products

Grundweiß LEF

Kieselit-Grundiermittel

This data sheet cannot deal with all types of application arising in practice. Therefore, we cannot be held responsible for their content. These instructions do not release the purchaser / applicator from his responsibility of professionally examining the substrate and determining the suitability of the product in consideration of the project characteristics. In case of queries please request the technical assistance of ALLIGATOR FARBWERKE.