

Super Weiß LEF

Dead matt dispersion-based interior paint of opacity class 1 and wet scrub resistance class 3.



Product characteristics

Properties	<ul style="list-style-type: none">• Easy to apply• Slightly filling• High covering power• Solvent- and plasticizer-free• Free of fogging-active substances• Emission test according to AgBB
Areas of application	Interior only
Suitable substrates in detail	<ul style="list-style-type: none">• All kinds of walls and ceilings in private or commercial areas.• Ideal as paint reinforcement in combination with ALLFAtexx-Anstrichvlies (GV 35)

Material description

Binder	Synthetic dispersion
Density	1.5 kg/l
Maximum particle size	Fine
Wet scrub class	2
Opacity class	1 at 6 - 7 m ² /L
Average consumption (short text)	approx. 140 - 170 ml/m ²
Average consumption	The consumption varies depending on the application technique and the substrate. It is therefore advisable to determine the exact consumption figure by producing a sample area.
Colour shade	White RAL 9010 RAL 9016 Base 3
Gloss level	Dead matt according to EN 13300
Storage	Cool, but protected from frost
Thinning	Water First and intermediate coat: 3%, finishing coat preferably unthinned.

Super Weiß LEF

Substrates

Suitable substrates

- All usual mineral substrates (renders/plasters, concrete, masonry)
- Gypsum wallboards and gypsum plasterboards
- Gypsum plaster
- Hardboards
- Precast building materials
- Adherent existing paint layers
- Wood-chip wallpaper
- Glass fabrics

Substrate conditions

The substrate must be clean, dry, firm and sound. Follow the building regulations (in Germany VOB, Part C, DIN 18363, Section 3). Inside renovation coatings can normally be carried out without a special priming coat. For new coatings the surface has to be first attended with an appropriate primer of the ALLIGATOR – product range, following the technical specifications.

Substrate conditions

Gypsum blocks

Adjust the primer to absorbency. With coatings destined to bridge capillary cracks, reinforce completely using a fleece. In addition the guidelines of BFS-Fact Sheet No. 17 apply.

Gypsum building boards (interior)

Adjust the primer to absorbency. With coatings destined to bridge capillary cracks, reinforce the entire surface using a fleece. In addition the guidelines of BSF Fact Sheet No. 12 apply. Ingredients which might penetrate have to be isolated before following coatings.

Gypsum plaster, gypsum sand plasters etc.

Remove any sintered layers. For first coatings take care of a sufficient penetration of the primer (e. g. by using a penetrating primer). Additionally the guidelines of BFS Fact Sheet No. 10 apply.

Derived timber products (chipboards, OSB-boards etc.) - interior

Have to be covered with a suitable gypsum board or gypsum fibre board as otherwise cracks may occur in the area of butt-joints.

Aerated concrete - interior:

In case of rooms of high humidity, external walls have to be additionally treated by a moisture guard, applied onto their insides. This can be effected applying a two-component coating like e.g. Hydrofox. In addition the guidelines of BFS Fact Sheet No. 11 apply.

Base renders (interior):

Mineral base renders must be thoroughly cured and dry, because otherwise discolouration, in particular with tinted following coats, may occur. As a rule of thumb assume 1 day drying time per mm of layer thickness, but correspondingly longer at low temperatures and high humidity. Excessive temperatures and low relative humidity also lengthen the setting process. Treat replastered locations with fluosilicate. In addition, the guidelines according to BFS Fact Sheet No. 10 apply.

Concrete

Remove forming oil, grease and wax by washing with surfactant. Remove any sintered layers mechanically. Check the absorbency of the concrete by wetting tests. In addition, the guidelines according to BFS Fact Sheet No.1 apply for exterior coatings and the guidelines according to BFS Fact Sheet No. 8 for interior coatings.

Application

Application method

Application by brush, roller or spraying

Spraying data

Suitable airless systems with an output of at least 3 l/min.

Airless: Spray pressure in bar: 160 - 190 / spraying angle: 50° / nozzle size in inch: 0.019 - 0.021 / filter: 60 mesh

Coating system

Initial coating

Priming coat with Tiefengrund LKF, Multi-Grund 3 in 1, Grundweiß LEF or Grundierfarbe WP.

Intermediate coating thinned to max. 3%.

Finishing coating: preferably unthinned

Super Weiß LEF

Recoatings

Priming coat with Multi-Grund 3 in 1, Grundweiß LEF or with Grundierfarbe WP. With sound and solid existing paint layers, an additional priming coat can be omitted.

Intermediate coating thinned to max. 3%.

Finishing coating: preferably unthinned

Due to the great varieties of our production range and individual applications, other primers and coating systems are possible. Please refer to our technical service for support.

Application

When painting pay attention to spread the material liberally and evenly in order to achieve a coat thickness which is necessary for the visual appearance and durability.

Application hints

In case of increased load two paint layers might be necessary.

Note

Check tinted paint for colour accuracy prior to the application. Objections regarding the colour shade cannot be accepted after the application.

The figures given for parameters are average values. Due to the use of natural raw materials in our products, the actual value determined on the individual supplied product may differ slightly without affecting its suitability. These data refer to the white respectively standard product. Tinting may cause deviations.

Plasto-elastic joints should not be coated as the higher elasticity of the sealing mass might cause cracks or discolouration of the coating. In individual cases tests have to be carried out to judge the suitability.

Practical hints

Repairs

Touching up surfaces may be more or less visible, even with using the original coating material. Traces are unavoidable according to BFS Fact Sheet No. 25. Whether a repair is considered as optically disturbing is depending on many parameters, like colour shade, gloss level, layer thickness, substrate, illumination etc. It is advisable to apply a test coating on inconspicuous places.

Brilliant and intensive Colour Shades

Brilliant and intensive colour shades may have a lower opacity due to the pigments used. The application of a first coat in a similar defined pastel tint (shown in online price recommendations and the ALLFAcolor tinting machine) normally avoids having to apply a layer on top of the standard rule of coating. On intensive shades in combination with matt / silk matt interior paints mechanical stress (scratching, rubbing) may result in bright stripes (writing effect). To avoid this effect in exposed areas, always use specifically designed interior paints.

Colour Accuracy / Metamerism

The perception of colour shades is influenced by various parameters, such as light, gloss, angle, structure. Substrates of different degrees of irregularities may have different effects despite having been coated with the same material. Coating materials of the same hue but of different gloss levels also appear to be different. Various materials of the same colour shade that appear to be matching by daylight may show strong deviations in artificial light (metamerism effect). In case of increased requirements on matching colours of different building parts, materials and / or surfaces, the BFS Fact Sheet No. 25, section 4.2.2. can be taken into consideration.

Fogging

The phenomenon of suddenly occurring black dust deposits on interior surfaces (fogging effect) has not yet been fully elucidated. As a preventive, the Federal Environment Agency (Umweltbundesamt) recommends to only use low-emission, in particular plasticizer-free products. These products are solvent- and plasticizer-free. The absence of fogging cannot be ensured.

New mineral Substrates

New mineral substrates may only be coated after setting and drying, not earlier than after 14 days, better after 4 weeks. In unfavourable drying conditions, the waiting period can be prolonged.

Non-combustibility

According to DIN 4102 (in Germany) the construction material class A (non-combustibility) is retained with usual mineral substrates such like renders/plasters, concrete and also gypsum plasterboard with enclosed surface, even if their surfaces are coated with dispersion based paints. For usability certificate as non-combustible system for interiors with ALLFAtextx glass fibres and fleeces refer to the general construction supervision test report.

Hairline Crack bridging Coatings on Gypsum Plasterboard

In correspondance with the building regulations (in Germany VOB/C DIN 18363, Section 3.2.1.2) hairline crack bridging coatings on gypsum plasterboards and gypsum fibreboards can only be realized by the additional embedding of a fleece.

Super Weiß LEF

Sidelight

Unfavourable lighting conditions (sidelight) may occur for instance after the subsequent installation of lights. This fact must be known before works. Specific requirements on evenness and uniformity of the coating have to be previously agreed upon.

Temperature limit

Between + 5° C and + 30° C for substrate and ambient air during processing and drying.

Drying time

At + 20° C for substrate and ambient air and 65% relative humidity (RH), recoatable after approx. 4 - 5 hours. Lower temperature or a higher humidity extend the drying time.

Tool cleaning

Immediately after use with water and soap

Information

Product code

BSW20 (M-DF01)

General information

Keep out of reach from children. Ensure good ventilation during use and drying. Do not eat, drink or smoke while using the painting works. In case of contact with eyes or skin, immediately and thoroughly rinse with water. Do not allow to enter drains, waterways or soil. Clean tools immediately with water and soap. Do not breathe vapour/spray.

Hazard statements and safety advice

May cause an allergic skin reaction. If medical advice is needed, have product container or label at hand. Keep out of reach of children. Do not get in eyes, on skin, or on clothing. Wear protective gloves/ eye protection. If on skin: Wash with plenty of soap and water. Contains: 2-methyl-2H-isothiazol-3-one

Declaration of ingredients

Poly vinyl acetate dispersion, titanium dioxide, calcium carbonate, silicates, water, additives, preservatives (methylisothiazolinone, benzisothiazolinone)

Observe safety data sheets

Further details: See Safety Material Data Sheet (MSDS)

Category VOC

EU limit value for the VOC contents of this product: (Category A/a) 30 g/l (2010). This product contains max.

VOC content (in gram per litre)

< 1 g/l

WHC

1 (weakly water-polluting)

Waste disposal

Only completely emptied containers should be given for recycling. Dispose containers with residues of liquid product via waste collection point accepting old paints and enamels. Dispose dried hardened product residues as construction site/demolition/ municipal or domestic waste.

Container size

Content		EAN code	Article no.
25 L	Weiß	4002822008611	972316
12,5 L	Weiß	4002822007164	972303
5 L	Weiß	4002822007270	972305
2,5 L	Weiß	4002822007317	972306
1,25 L	Weiß	4002822007355	972308
11,75 L	Basis 3	4002822007461	972312
4,7 L	Basis 3	4002822007492	972313
2,35 L	Basis 3	4002822007515	972314
1,175 L	Basis 3	4002822008598	972315
12,5 L	RAL 9010	4002822007188	972304
12,5 L	RAL 9016	4002822008635	972431
15 L	RAL 9016	4002822018375	984954

Super Weiß LEF

System specific and system completing products

Grundweiß LEF

Tiefgrund LKF

This data sheet cannot deal with all types of application arising in practice. Therefore, we cannot be held responsible for their content. These instructions do not release the purchaser / applicator from his responsibility of professionally examining the substrate and determining the suitability of the product in consideration of the project characteristics. In case of queries please request the technical assistance of ALLIGATOR FARBWERKE.